



Application of in situ oxidation-resistant coating technology to a home-made 100 kW class gas turbine and its performance analysis

Min Tae Kim^{a,*}, Si Woo Lee^{b,1}

^a Power Generation Laboratory, Korea Electric Power Research Institute, 105 Munji-Ro, Yuseong-Gu, Daejeon 305-380, Republic of Korea

^b Jinsol Turbomachinery, Daejeon 306-220, Republic of Korea

ARTICLE INFO

Article history:

Received 2 November 2011

Accepted 14 February 2012

Available online 21 February 2012

Keywords:

Micro-gas turbine
In situ deposition
Silica coating
Performance
Efficiency

ABSTRACT

An axial type 100 kW class gas turbine power generation system equipped with an additive supply system was fabricated and tested for the performance evaluation experimentally and analytically, in order to confirm the advantage of in situ oxidation-resistant coatings on gas turbine components toward the performance of a gas turbine power generation system directly. The gas turbine was operated up to the rated speed of 74,000 rpm, and to the turbine inlet temperature (TIT) of ~ 1200 °C. At the early stage of this test operation, an oxide film precursor (tetraethylorthosilicate/methanol mixture, 10 vol.%) was fed into the combustion chamber by the additive supply system to in situ deposit silica based layers and thus to protect the metallic components from hot combustion gas during operation. After the test operation, in situ deposited silica layers were observed on the surface of the combustion chamber, turbine nozzles and rotor blade. Due to these protective layers the gas turbine could be harmless tested at TIT = 950 °C, much higher than its design temperature of 850 °C. According to the performance analysis, a TIT increase of 100 °C was expected to be accompanied by $\sim 5\%$ increase in the turbine rotation speed by consuming more fuel and air by 22% and 8%, respectively. As a result, the power output increased by 42% and the thermal efficiency from 12% to 14%. This result was well accorded with that of empirically obtained, indicating that no noticeable impacts on the performance due to in situ deposited layers on the components.

© 2012 Elsevier Ltd. All rights reserved.

1. Introduction

Small gas turbines with output power less than ~ 300 kW are often referred to as microturbines or micro-gas turbines (MGTs). The TIT of MGTs is typically in the range of 800–1000 °C, the maximum service temperature that the metallic components can tolerate for a long time operation without cooling [1]. The TIT can be further raised by applying sophisticated component design (e.g. cooling holes in the blades [2,3]) and thermal barrier coatings, TBC [4–6], which are adopted by most heavy duty land-based gas turbines these days. For MGTs, however, TBCs cannot easily be applied to the hot gas components due to dimensional problems and to complicated design (to our knowledge, there are no MGTs with TBCs applied on the metallic components, yet). Due to this limitation, the thermal efficiency of MGTs lies in the middle of 20%,

though it has been raised above 30% recently by incorporating highly effective recuperation systems [7].

A coating technology applicable to MGTs was proposed and studied recently [8–11]. This technology was characterized by in situ deposition of oxide-base protective layers on the surface of all the components exposed to hot combustion gas by feeding oxide film precursors into the combustion chamber during service. The in situ deposited layers effectively protected the underlying metallic substrates during operation, as demonstrated by metallographic studies on Inconel 713 superalloy blades [9–11]. These results were attributed partly to thermal insulation of the outer highly porous layer and partly to diffusion inhabitation of the inner thin solid layer. Very recently [12], the effect of the periodic deposition of such protective layers on the long term reliability of a very small gas turbine (~ 10 kW) undergone to a cyclic operation was tested in our group. The test results showed that the in situ deposited hot gas components could tolerate metallographically an increase in the TIT of 100 °C for a long time. In this work, we further took advantage of the thermal and diffusion barrier of in situ deposited oxide coatings further to raise the TIT of a home-made 100 kW class gas

* Corresponding author. Tel.: +82 42 865 5681; fax: +82 42 865 5365.

E-mail addresses: mtkim@kepri.re.kr (M.T. Kim), impentacle@jinsolturbo.co.kr (S.W. Lee).

¹ Tel.: +82 42 931 6518; fax: +82 42 931 6519.